



## SCX-13

# JOINTING AND HEATSINK THERMAL COMPOUND

### DESCRIPTION

SCX-13 contains prime grade zinc and is formulated with 50% metallic zinc to create a compound that enhances electrical and thermal conductivity when used on high power Jointing, Heatsink, Crimp connections and Stud bolt mountings.

When the connection is tightened, the grease is displaced, leaving a layer of zinc filling in the surface imperfections of the interface. This has a twofold effect: it improves the electrical conductivity and it improves thermal conductivity. This reduces the connection temperature under high power conditions by a reduced voltage drop and by providing a heat conductivity path to the connection's substrate.

SCX is manufactured with a unique grease compounded from custom refined low sulphur oil. The grease base ensures brushability over a wide temperature range, tenacious adherence to all surfaces, resistance to water wash out and the prevention of rust/corrosion. This makes the product easier and more reliable to use.

### ADVANTAGES

- Makes connections more reliable
- Makes connections more weatherproof
- Protects connections from corrosion
- Reduces temperature rise
- Low sulphur content
- Non-reactive, no gassing in storage
- Brushable over a wide temperature range
- Sticks to wet joints

### PRODUCT CHARACTERISTICS

Thickener	Bentone
Fluid Type	Petroleum
Colour/Appearance	Smooth Grey Paste
Dropping Point (ASTM D-566)	None
Specific Gravity	1.78
Oil Separation	<5.0
Wt. % Loss @ 212°F (100°C)	
Flash Point (ASTM D-92)	>221°C (430°F)
NLGI Grade	1-2
Penetration @ 77°F (ASTM D-217)	275-305
Copper Strip Corrosion (ASTM D-4048)	1A
Service Rating: -18°C (0°F) to 370°C (700°F)	

### PACKAGING

Code No.	Size	Container
SCX13/1Kg	1 Kg	Tub
SCX13/100g	100g	Tube

**GD Rectifiers Ltd.** Victoria Gardens, Burgess Hill, West Sussex  
RH15 9NB.

**Tel: 01444 243452 Fax: 01444 870722**

**E-Mail: [enquiries@gdrectifiers.co.uk](mailto:enquiries@gdrectifiers.co.uk) Web Site: [www.gdrectifiers.co.uk](http://www.gdrectifiers.co.uk)**